

KYNAR FLEX®

PPA 5300

Kynar Flex® resins are fluorinated thermoplastic copolymers.

Kynar Flex® PPA 5300 resin is specially designed pellet used as a polymer process aid (PPA) for polyolefins.

The use of Kynar Flex® PPA 5300 resin at 200 - 1000 ppm levels reduces extruder pressure, improves surface finish, reduces die build up, and improves gauge control.

This product is also available on a powder form as Kynar Flex® PPA 5301 resin.

PROPERTIES	VALUE	UNIT	TEST STANDARD
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	165	°C	ISO 11357-1/-3
Melting Point	≤329	°C	ASTM D3418
OTHER PROPERTIES			
Density	700	kg/m ³	ISO 1183
	0.7	g/cm ³	
Bulk Density	0.5 - 0.9	g/cm ³	1% wt. loss

PROCESSING Film Extrusion, Sheet Extrusion, Other Extrusion	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
DELIVERY FORM Granules, Powder	
REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa	
	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.