

PEBAX[®]

MV 1074 SA 01

Polyether block amide **Pebax[®] MV 1074 SA 01 resin** is a thermoplastic elastomer made of flexible and hydrophilic polyether and rigid polyamide.

Pebax[®] MV 1074 SA 01 resin is also an inherently dissipative polymer and can be dry blended or compounded with a polymer matrix to lower the surface resistivity of the final part.

This hydrophilic grade when extruded into either a thin film or laminated on to a substrate offers excellent permeability to moisture vapor while remaining waterproof .

This SA grade is specially designed to food uses.

Refractive index according to an internal method is 1.502.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
MECHANICAL PROPERTIES			
Tensile Modulus	97 / 80	MPa	ISO 527-1/-2
	14100 / 11600	psi	
Stress at 50% Strain	10 / 10	MPa	ISO 527-1/-2
	1450 / 1450	psi	
Strain at Break	>50 / >50	%	ISO 527-1/-2
Strain at Break TPE	>300 / *	%	ISO 527-1/-2
Stress at Break TPE	30 / *	MPa	ISO 527-1/-2
	4350 / *	psi	
Shore D Hardness, after 15 s	38 / *	-	ISO 868
Charpy Impact Strength, +23°C	No Break / No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	No Break / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	No Break / No Break	kJ/m ²	ISO 179/1eA
Charpy Notched Impact Strength, -30°C	No Break / -	kJ/m ²	ISO 179/1eA
Maximum Stress, parallel	32 / *	MPa	ISO 527-3
	4640 / *	psi	
Maximum Stress, normal	34 / *	MPa	ISO 527-3
	4930 / *	psi	
Maximum Strain, parallel	500 / *	%	ISO 527-3
Maximum Strain, normal	700 / *	%	ISO 527-3
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	158 / *	°C	ISO 11357-1/-3
Glass Transition Temperature, 10°C/min	-40 / *	°C	ISO 11357-1/-2
Oxygen Index	19 / *	%	ISO 4589-1/-2
ELECTRICAL PROPERTIES			
Volume Resistivity	1.5E9 / 2.5E7	Ohm* m	IEC 62631-3-1
Surface Resistivity	* / 3E9	Ohm	IEC 62631-3-2

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 12-08-2024

PEBAX[®]

MV 1074 SA 01

Dielectric (Electric) Strength	5 / -	kV/mm IEC 60243-1
	127 / -	kV/in

OTHER PROPERTIES

Humidity Absorption, 23°C, RH50%, equilibrium	1.4 / *	% ISO 62
Density	1070 / -	kg/m ³ ISO 1183
	1.07 / -	g/cm ³

MAIN APPLICATIONS:

- Breathable membranes
- Permanent antistatic additive
- Note: this grade is not recommended by Arkema for usage in medical applications. For such applications Pebax[®] SA 01 MED should be used

PACKAGING:

This grade is delivered dried in sealed packaging (25 kg bags and 550 kg rigid containers) ready to be processed.

SHELF LIFE:

Two years from the delivery. For any use above this limit, please refer to our technical services.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max): 200°C / 240°C / 270°C.
- Typical mold temperature: 25–60°C.
- Drying time and temperature (only necessary for bags opened for more than two hours): 4-6 hours at 65-75°C.

Processing conditions:

- Typical melt temperature (Min / Recommended / Max): 210°C / 220°C / 230°C.
- Drying time and temperature (only necessary for bags opened for more than two hours): 4-6 hours at 65-75°C.

PROCESSING	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
Injection Molding, Other Extrusion	
DELIVERY FORM	
Pellets	
SPECIAL CHARACTERISTICS	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
Anti-Static, Heat Stabilized	
REGIONAL AVAILABILITY	
North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
 Source: automatically generated TDS from Material Database on 12-08-2024

PEBAX[®]

MV 1074 SA 01

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.