

RILSAN® BESVO A MED

PA11, E, 22-010

Rilsan® BESVO A MED resin is a polyamide 11 produced from a renewable source. This natural grade, dedicated to extrusion, contains a negligible amount of oligomers. **Rilsan® BESVO A MED resin** offers the highest quality and it is specially designed to meet the stringent requirements of the medical applications such as minimally invasive devices.

Upon request letters regarding USP Class VI compliance can be provided.

PROPERTIES	DRY / COND	UNIT	TEST STANDARD
RHEOLOGICAL PROPERTIES			
Melt Volume-Flow Rate	6 / *	cm ³ /10 min	ISO 1133
Temperature	235 / *	°C	-
	455 / *	°F	-
Load	10 / *	kg	-
	22 / *	lb	-
Molding Shrinkage, parallel	1.1 / *	%	ISO 294-4, 2577
Molding Shrinkage, normal	1.1 / *	%	ISO 294-4, 2577
MECHANICAL PROPERTIES			
Tensile Modulus	- / 1180	MPa	ISO 527-1/-2
	- / 171000	psi	
Yield Stress	- / 36	MPa	ISO 527-1/-2
	- / 5220	psi	
Yield Strain	- / 5	%	ISO 527-1/-2
Nominal Strain at Break	- / >50	%	ISO 527-1/-2
Shore D Hardness, after 15 s	71 / *	-	ISO 868
Charpy Impact Strength, +23°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Impact Strength, -30°C	- / No Break	kJ/m ²	ISO 179/1eU
Charpy Notched Impact Strength, +23°C	- / 15	kJ/m ²	ISO 179/1eA
	- / 7.14	ftlb/in ²	
Charpy Notched Impact Strength, -30°C	- / 13	kJ/m ²	ISO 179/1eA
	- / 6.18	ftlb/in ²	
THERMAL PROPERTIES			
Melting Temperature, 10°C/min	186 / *	°C	ISO 11357-1/-3
Oxygen Index	25 / *	%	ISO 4589-1/-2
ELECTRICAL PROPERTIES			
Dielectric (Electric) Strength	- / 30	kV/mm	IEC 60243-1
	- / 762	kV/in	
OTHER PROPERTIES			

Arkema France - A French "société anonyme", registered in the Nanterre (France) Trade and Companies Register under the number 319 632 790 SDC/11-2018
Source: automatically generated TDS from Material Database on 20-02-2024

RILSAN[®]

BESVO A MED

Water Absorption, 23°C, immersion, equilibrium	1.9 / *	%	ISO 62
Density	1030 / 1030	kg/m ³	ISO 1183
	1.03 / 1.03	g/cm ³	

MAIN APPLICATIONS:

- Nutritional bags
- Catheters

PACKAGING:


This grade is delivered dried in sealed packaging (25 kg bags) ready to be processed.

SHELF LIFE:


Two years from the delivery. For any use above this limit, please refer to our technical services.

DIAGRAMS

VISCOSITY-SHEAR RATE




SHEARSTRESS-SHEAR RATE




RILSAN® BESVO A MED

STRESS-STRAIN



SECANT MODULUS-STRAIN



Processing conditions:

- Typical melt temperature (Min / Recommended / Max) : 230°C / 250°C / 280°C.

- Drying time and temperature (only necessary for bags opened for more than two hours) : 4-6 hours at 65-80°C.

PROCESSING Injection Molding, Film Extrusion, Profile Extrusion, Other Extrusion	Headquarters: Arkema France 420 rue d'Estienne d'Orves 92705 Colombes Cedex France T +33 (0)1 49 00 80 80 hpp.arkema.com
DELIVERY FORM Pellets	
SPECIAL CHARACTERISTICS Bio-Based	Arkema Inc. – High Performance Polymers 900 First Avenue King of Prussia, PA 19406 Tel.: +1 610 205 7000 hpp.arkema.com
REGIONAL AVAILABILITY North America, Europe, Asia Pacific, South and Central America, Near East/Africa	

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.